




DESCRIPTION			
Total thickness	EN ISO 24346	mm	2.00
Thickness of wearlayer	EN ISO 24340	mm	0.70
Weight	EN ISO 23997	g/m ²	2635
Width of sheet	EN ISO 24341	cm	200
Length of sheet	EN ISO 24341	lm	25
CLASSIFICATION			
Norm / Product specification	-	-	EN ISO 10582
European classification	EN ISO 10874	class	34 - 43
Fire rating	EN 13501-1	class	B _{fl} -s1
Static electrical propensity	EN 1815	kV	< 2
Slip resistance : Pendulum Test (1)	EN 16165:2021 – Appendix C (BS 7976-2)	PTV	> 36
Surface roughness R _{tm}	-	µm	R _z ≥ 20
Slip resistance wet: ramp test	EN 16165:2021 – Appendix B (DIN 51 130)	class	R11
PERFORMANCES			
Wear resistance	EN 660.2	mm ³	≤ 2.0
Wear group	NF 189	group	T
Type Binder content	EN ISO 10582	type	I
Dimensional stability	EN ISO 23999 (EN 434)	%	≤ 0.40
Residual indentation (requirement)	EN ISO 24343-1 (EN 433)	mm	≤ 0.10
Residual indentation (measure)	-	mm	≈ 0.03
Impact sound insulation	EN ISO 717-2	dB	8
Castor chair test (type W)	EN ISO 4918	-	OK
Thermal conductivity	EN ISO 10456	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Surface treatment	-	-	Protocolsol® Control
Chemical products resistance	EN ISO 26987	-	OK
Anti-bacterial activity (E. coli – S. aureus -MRSA) (2)	ISO 22196	-	> 99% Inhibits growth
ENVIRONMENT / INDOOR AIR QUALITY			
TVOC after 28 days	ISO 16000-6	µg/ m ³	< 70
Certification	-	-	Floorscore®
CE MARKING			
	EN 14041		
			

(1) The RRL pendulum test : wet is expressed as a pendulum test Value (PTV) and a Slip Resistance Value (SRV) to show that the test was carried out using a 4S rubber resistor pad in accordance HSE (for lifetime sustainable wet resistance, please refer to Tarasafe ranges)

(2) The implementation of an effective cleaning regime is the best defence against infection